



WEATHERPROOF™
Rubberized Damp Surface Foundation Coating
#41345

A tough, high quality foundation coating manufactured with specially selected asphalt, fibers, surfactants, and butyl rubber. Specially formulated for penetration and adhesion to damp or dry substrates. It can be easily applied by spray or brush. Applied as directed, it cures to a durable, crack resistant, weatherproof seal. Damp proofs below grade vertical, exterior poured concrete or masonry foundation walls. Meets all the requirements of ASTM D 4479.

Uses

- Below grade dampproofing for exterior poured concrete or masonry surfaces.

Advantages

- Rubberized for increased flexibility.
- Can be used on damp surfaces.
- Goes on thicker than conventional no fiber foundation coatings, thereby offering greater protection against the entrance of moisture.
- Can be used with 2 ounce polyester mat to form an economical dampproofing system.

INSTALLATION

Coverage

- Product yield to achieve desired rate will be from 1.0 to 3 gallons per 100 square feet. The yield varies according to the existing surface texture. As a general rule, the smoother the surface, the less material is required.
- Recommended application rate is 16 to 48 mils wet film thickness which will produce 12 to 36 mils dry. A mil is 1/1000 of an inch.

Surface Preparation

- Remove all dirt, dust, debris, mud, oil, grease, and other foreign matter which may prevent proper adhesion. Fill all voids and repair cracks before applying coating.

Application

- Apply with a roofing brush or sprayer. Be sure to spread product evenly.
- Clean up tools and equipment with mineral spirits, but do not thin the product.
- If the product is difficult to spread in cooler temperatures, warm containers by storing them overnight in a room at 65° to 75° F.

Drying Time

- Four hours to touch at 70° F. and 50% relative humidity. Allow the coating to dry a minimum of 48 hours before back filling.

Restrictions

- Do not use where material, once applied, may come in contact with potable water.
- Not for use on or with products containing coal tar.
- Do not use on slate shingles or apply directly to wood surfaces.
- Surfaces to be coated must be dry or damp. Standing water or thoroughly soaked substrates will impair adhesion. Coated areas must remain dry for 24 to 48 hours after application.
- Not for use over rubber or plastic membranes - asphalt modified only.
- For exterior use only.

Cautions

- This product is combustible. Keep away from heat, sparks, and open flame. Avoid breathing of vapors or spray mist. Avoid repeated or prolonged contact with skin. If swallowed, do not induce vomiting. Contact Physician immediately. Keep container closed when not in use. **KEEP AWAY FROM CHILDREN.** Product label and Material Safety Data Sheet contain further information on the safe use of this product and precautions for the safe disposal of the container. They should be read and understood prior to use.

SPECIFICATIONS

Percent Solids by Weight minimum	75%
Percent Solids by Volume minimum	69%
Weight per Gallon: Pounds.....	8.7
Flash Point minimum	105° F (Seta C.C.)
P.H.....	N/A
Viscosity at 77° F.....	22,500 cps.
Long-Term Service Temperature	-60° F. to +160° F.
Water Resistance: Intermittent Exposure	Excellent
Water Resistance: Ponded	Fair
Solvent Resistance	Poor
U.V. Resistance	Good
VOC	< 250 grams/liter

<u>Product Number</u>	<u>Size</u>	<u>Quantity</u>	<u>Weight</u>
41345	5 Gal.	Each	45 lbs.