



WEATHERPROOF™
Wet/Dry Foundation Mastic-Trowel Grade
#41405

A heavy bodied blend of carefully selected asphalts, solvents, fibers, and surfactants. It can be used with a reinforcing fabric for below grade waterproofing of vertical surfaces. Foundation Mastic is formulated for trowel application. Once cured, it forms a tough, durable protective coating for vertical concrete, masonry and metal surfaces.

Uses

- A waterproofing treatment when used with 20 x 10 fiberglass or 2 ounce polyester fabric reinforcement.
- A dampproofing protective coating when used alone.

Advantages

- Will not run or sag.
- Fills small cracks and chips.
- Unaffected by mold and mildew.

INSTALLATION

Coverage

- Product yield to achieve desired rate will be from 3 to 4 gallons per 100 square feet per coat. The yield varies according to the existing surface texture. As a general rule, the smoother the surface, the less material is required.
- Recommended application rate per coat is 48 to 64 mils wet film thickness which will produce 37 to 50 mils dry. A mil is 1/1000 of an inch.

Surface Preparation

- Remove all loose materials, dirt and dust from surface to be coated. Heavy deposits and stains should be wire brushed and broomed. Make certain that surface is dry.

Application

- Trowel material onto surface in a smooth, even layer. For fabric reinforced application, imbed glass or polyester in freshly applied material in vertical strips. Overlap each strip by approximately 4 inches on the

Application (continued)

sides. Allow 24 to 48 hours curing time before applying the second coat depending upon weather. (With or

without fabric)

- Clean up with mineral spirits, but do not thin the product with this or any other solvents.
- If the product is difficult to spread in cooler temperatures, warm containers by storing them overnight in a room at 65° to 75° F.

Drying Time

- Four hours to touch at 70° F. & 50% relative humidity per coat. Twenty-four to 48 hours is required for thorough evaporation of solvent. Cool or overcast weather slows drying. Hot, dry weather with strong air circulation provides optimum drying conditions. (See Restrictions.)

Restrictions

- Do not use with PVC film.
- Do not use where material, once applied, may come into contact with potable water.
- Surfaces to be coated must be dry and clean and must remain so for 24 to 48 hours after application for each coat.
- Do not back fill until mastic is dry.
- Do not use on wood.
- For exterior use only.

Cautions

- This product is combustible. Keep away from heat, sparks and open flame. Avoid repeated or prolonged contact with skin. If swallowed, do not induce vomiting. Contact Physician immediately. Keep container closed when not in use. **KEEP AWAY FROM CHILDREN.** Product label and Material Safety Data Sheet contain further information on the safe use of this product and precautions for the safe disposal of the container. They should be read and understood prior to use.

Percent Solids by Weight	78%
Percent Solids by Volume	72%
Weight Per Gallon: Pounds ...	9.37
Flash Point minim.....	105° F. (Seta C.C.)
P.H.....	N/A
Viscosity at 77° F.	640,000 cps.
Mildew Resistance: ...	Excellent
Water Resistance: Intermittent Exposure.....	Excellent
Water Resistance: Continuous Immersion	Good
VOC	<250 grams/liter

SPECIFICATIONS

<u>Product Number</u>	<u>Size</u>	<u>Quantity</u>	<u>Weight</u>
41405	5 Gal.	Each	50 lbs.