



DRIVEGUARD™
Liquid Asphalt Crack Filler
#51601

A smooth, uniform mixture of modified emulsified asphalt, clay and other selected fillers. Designed for filling cracks up to 1/2" wide in asphalt or concrete pavements. It requires no heating for application. It is packaged in a convenient, easy to use plastic bottle with a removable spout. This flexible packaging allows the material to be squeezed directly into the opening of the crack.

Uses

Use to fill cracks in asphalt or concrete pavements.

Advantages

- Easy to use squeeze bottle with spout.
- Seals moisture out of cracks preventing damage to pavement base.
- Prevents small cracks from becoming large ones.

INSTALLATION

Coverage

30 lineal feet of crack at 1/2 inch wide and 1 inch deep.

Surface Preparation

Remove dirt, debris, or vegetation from crack with a stiff brush or water pressure. Deep cracks (deeper than one inch) should be filled in two applications or sand or backer rod can be used to fill the crack to within 1/2 inch from the surface. The surface may be dry or damp, with no standing water.

Application

- Apply only when ambient and pavement temperatures exceed 50°F and will remain above for 24 hours. Apply when no precipitation is likely for 24 hours. Crack filler can be washed out of cracks if it rains before it dries and hardens.

Application (continued)

- Handshake the bottle vigorously until a uniform mix is obtained. Invert the spout from inside of bottle, wipe clean and cut to desired opening size. Insert spout opening into crack and squeeze the bottle while moving it along the length of the crack. Amount of pressure and speed of movement will determine the amount applied. Always force material to the bottom of the crack to ensure a good bond.
- Clean up with water while material is still wet. After the product has dried use mineral spirits.

Drying Time

Four hours to touch at 70° F. & 50% relative humidity. Never apply material if rain is imminent or forecast. Material that has not set will be washed away by a moderate rain.

Restrictions

- Do not use where material, once applied, may come in contact with potable water.
- Do not apply when rain is imminent or forecast.
- Allow crack filler to cure for approximately one week before applying a coat of driveway sealer.
- For exterior use only.
- Protect from freezing. Crack filler is ruined if frozen.

Cautions

Avoid breathing of vapors. Avoid repeated or prolonged contact with skin. If swallowed, do not induce vomiting. Contact Physician immediately. Keep container closed when not in use. **KEEP AWAY FROM CHILDREN.** Product label and Material Safety Data Sheet contain further information on the safe use of this product and precautions for the safe disposal of the container. They should be read and understood prior to use.

SPECIFICATIONS

Non-Volatiles Percentage by Weight	48%
Ash of Non-Volatiles Percentage by Weight	51%
Weight Per Gallon: Pounds.....	10.10
Flash Point.....	N/A
P.H.	7.1
Viscosity at 77° F.	8,000 cps.
Resistance to Oils.....	Good
Resistance to Gasoline... ..	Good
Resistance to Surface Water.....	Excellent

PACKAGING INFORMATION

<u>Product Number</u>	<u>Size</u>	<u>Quantity</u>	<u>Weight</u>
51665	5 Gal.	EACH	50 lbs.
51601	1 Gal.	Case of 6	60 lbs.